



## **Chemblend FFD0062**

*Blowing Agent Concentrate for Use in Polyethylene and Polypropylene*

**Appearance:**

White Pellet

**Description:**

Metal Organic Compound

**Technical Data:**

Percent of Active Blowing Agent:	20%
Decomposition Temperature:	150°C to 200°C
Gas Yield of Concentrate:	27 ml/gm at 250°C

**Properties:**

- Dust Free Pellet
- Compatibility with PE and PP
- Endothermic Decomposition
- No Plate Out on Screw and Mold
- Uniform Foam Structure

**Application:**

- Injection Molding
  - o Antisink, Structural Foam Parts and Weight Reduction

**Recommended Use Levels:**

- Injection Molding
  - o Antisink 0.5% to 5.0%

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.