

Product Description					
High Flow Nylon 6, Heat Stabilized with Internal and External Lubricants					
General Properties					
Appearance	Black, Natural and Colors				
Processing Methods	Injection Molding				
Applications	Automotive, Material Handling, Industrial				
Mechanical Properties	Test Method	English Units		S.I. Units	
Tensile Strength @ Yield	ASTM D638	11,500	psi	79	MPa
Tensile Elongation at Break	ASTM D638	50	%	50	%
Flexural Modulus	ASTM D790	420,000	psi	2,897	MPa
Flexural Strength	ASTM D790	16,000	psi	110	MPa
Notched Izod Impact (73°F)	ASTM D256	1.0	ft-lb/in	53	J/m
Physical Properties	Test Method	English Units		S.I. Units	
Specific Gravity	ASTM D792	1.13	sp gr	1.13	sp gr
Filler Content		0.0	%	0.0	%
Thermal Properties	Test Method	English Units		S.I. Units	
Heat Deflection Temperature @ 264 psi	ASTM D648	145	°F	63	°C
Injection Molding		Value			
Drying Temperature		180	°F		
Drying Time		2.0 - 4.0	hrs		
Maximum Drying Time		4	hrs		
Suggested Maximum Moisture		0.02	%		
Rear Barrel Temperatures		470 - 520	°F		
Middle Barrel Temperatures		480 - 530	°F		
Front Barrel Temperatures		490 - 540	°F		
Nozzle Temperature		490 - 540	°F		
Melt (processing) Temperatures		490 - 540	°F		
Mold Temperatures		130 - 200	°F		

These Data Sheet Values are Typical Values and are not intended for specification purposes. These values should only be used as a guide and no assurances by EnCom, Inc. can be granted that all molded articles will exhibit duplicate properties as those listed above. Each material user should perform their own testing for suitability.