

Product Description					
Low Gloss ASA					
General Properties					
Appearance	Natural, Black, Colors				
Processing Methods	Injection Molding				
Applications	Automotive, Industrial, Lawn & Garden				
Mechanical Properties	Test Method	English Units		S.I. Units	
Tensile Strength @ Yield	ASTM D638	6,000	psi	41	MPa
Tensile Elongation at Break	ASTM D638	4.40	%	4.40	%
Flexural Modulus	ASTM D790	325,000	psi	2,241	MPa
Flexural Strength	ASTM D790	10,000	psi	69	MPa
Notched Izod Impact (73°F)	ASTM D256	3.0	ft-lb/in	160	J/m
Physical Properties	Test Method	English Units		S.I. Units	
Specific Gravity	ASTM D792	1.05	sp gr	1.05	sp gr
Melt Flow 230°C/3.8 kg	ASTM D1238	1.5	g/10min	1.5	g/10min
Mold Shrink - Flow: 0.126 in (3.20 mm)	ASTM D955	0.006	in/in	0.006	mm/mm
Mold Shrink -XFlow: 0.126 in (3.20 mm)	ASTM D955	0.006	in/in	0.006	mm/mm
Rockwell Hardness (R-Scale)	ASTM D785	108		108	
Flame Rating 0.062	UL 94	HB		HB	
Thermal Properties	Test Method	English Units		S.I. Units	
Heat Deflection Temperature @ 264 psi	ASTM D648	180	°F	82	°C
Injection Molding		Value			
Drying Temperature		180 - 200	°F		
Drying Time		2.0 - 4.0	hr		
Maximum Drying Time		7	hr		
Suggested Maximum Moisture		0.10	%		
Rear Barrel Temperatures		370 - 450	°F		
Middle Barrel Temperatures		400 - 475	°F		
Front Barrel Temperatures		425 - 500	°F		
Nozzle Temperature		425 - 525	°F		
Melt (processing) Temperatures		425 - 525	°F		
Mold Temperatures		90 - 160	°F		
Back Pressure		25 - 100	psi		
Screw speed		25 - 75	rpm		

These Data Sheet Values are Typical Values and are not intended for specification purposes. These values should only be used as a guide and no assurances by EnCom, Inc. can be granted that all molded articles will exhibit duplicate properties as those listed above. Each material user should perform their own testing for suitability.

EnCom Polymers, Inc.

812-421-7700 • www.encompolymers.com